

EGL170-8

EGL SERIES | SUPREME DEEP CYCLE AGM

CYCLING CAPACITY

20 Hour Rate	**170 Amp Hours**

RESERVE CAPACITY

Reserve @25 AMPS	**330 Minutes**	Reserve @56 AMPS	**120 Minutes**

ELECTRICAL SPECIFICATIONS

Nominal Voltage	**8 Volt**
C100	**187AH**
C20	**170AH**
C10	**149AH**
C5	**140AH**
C3	**117AH**
C2	**112AH**
C1	**102AH**
Internal Resistance	**2.5m Ω**

MECHANICAL SPECIFICATIONS

Group Size	**GC8**	
Terminal Type	**M8**	
Terminal Torque	**See reverse side**	
Height (w/ terminal)	**11.35"**	**288 mm**
Height (case only)	**11.35"**	**288 mm**
Width	**7.17"**	**182 mm**
Length	**10.25"**	**260 mm**
Weight	**81.57 lbs.**	**37 kg**
Case Type	**ABS Plastic -** Flame Res. Rating UL94-HB	

DISCHARGE TABLE (Constant Current)

Time	Amps	Rate
20hr	8.5	0.05CA
10hr	14.9	0.10CA
8hr	17.8	0.13CA
5hr	28	0.20CA
3hr	39.1	0.33CA
2hr	56	0.50CA
1hr	96	1.00CA

DISCHARGE PROFILE (Constant Current)

8-Volt Battery *Temperature: 77°F (25°C)*



- All listed ratings are @ 100% SoC, T=77°F (25°C), 1.75VPC unless otherwise specified.
- Specifications listed are for estimation purposes only. Battery performance can vary depending on application. Battery design subject to change.

BATTERY & TERMINAL DIMENSIONS (All units shown in mm)







Battery bank spacing required, 12.5mm (1/2" inch) minimum

Terminal: M8



(unit: mm)

fullriverbattery.com

TEMPERATURE vs CAPACITY



STATE of CHARGE (SOC) vs OPEN CIRCUIT VOLTAGE (OCV)



CYCLE LIFE vs DEPTH of DISCHARGE (DOD) *(Based on BCI Testing @ 2-hr Rate)



SELF DISCHARGE vs TIME/TEMPERATURE



Note: "Boost Charge" required @ 75% SoC, Max 50% Soc

baterias.com

TEMPERATURE RANGE SPECIFICATIONS

Condition	Recommended	Maximum	Recommended	Maximum
Storage	5°F to 122°F	-40°F to 160°F	-15°C to 50°C	-40°C to 71°C
Operation	5°F to 104°F	-40°F to 160°F	-15°C to 40°C	-40°C to 71°C
Charge with TC	5°F to 122°F	-40°F to 160°F	-15°C to 50°C	-40°C to 71°C
Charge w/o TC	32°F to 104°F	5°F to 122°F	0°C to 40°C	-15°C to 50°C

***TC=** Temperature Compensation*

CHARGE VOLTAGES

	Battery Voltages			
Charge Stage	**8V**	**24V**	**32V**	**48V**
Bulk	9.8V	29.4V	39.2V	58.8V
Absorption	9.8V	29.4V	39.2V	58.8V
Float	9.1V	27.3V	36.4V	54.6V

TC Factor: (-2mV/°F/cell) or (-4mV/°C/cell)

TERMINAL TORQUE SPECS (applicable values are highlighted)

M6	M8	M10	M6M (Stud)	M8M (Stud)	M10M(Stud) & 3/8" Stud	FR45	TP06 (AP)	TP08/TP68 (AP)	AP
3.3-4.8ft-lbs	5.2-6.7ft-lbs	8.1-10.3ft-lbs	2.6-3.7ft-lbs	4.4-5.9ft-lbs	7.4-8.8ft-lbs	4.8-6.3ft-lbs	2.6-3.3ft-lbs	4.6-6.3ft-lbs	4.2-5.8ft-lbs
40-57.5lbs-in	62-80lbs-in	97-124lbs-in	31-44lbs-in	53-71lbs-in	88.5-106lbs-in	57-75lbs-in	31-40lbs-in	55-75lbs-in	50-70lbs-in
4.5-6.5Nm	7-9Nm	11-14Nm	3.5-5Nm	6-8Nm	10-12Nm	6.5-8.5Nm	3.5-4.5Nm	6.2-8.5Nm	5.6-7.9Nm

ISO CERTIFIED

9001:2008 Quality Management System
14001:2004 Environmental Management System
18001:2007 Occupational Health & Safety Management System

DEEP 100% CYCLE

DELIVERY APPROVED!
LAND, SEA & AIR

Fullriver batteries are sealed lead acid batteries made with Absorbed Glass Mat (AGM) technology. The electrolyte is absorbed into the fiberglass separator material rather than in a free-flowing liquid form. Fullriver batteries are non-spillable electric storage batteries. They are excepted from the requirements of DOT's hazardous materials regulations, since they adhere to the requirements of code 49 CFR Section 173.159(D) - **(CLASSIFIED APPROVED: DOT, CFR, HMR49, IATA, ICAO67, IMDG27)**